

Glove Compatibility

	Chemicals	Latex	Nitrile	Chloroprene**	Chemicals	Latex	Nitrile	Chloroprene**
*	ACETALDEHYDE	G	G	VG	KEROSENE	F	VG	VG
	ACETIC ACID	VG	VG	VG	KETONES	VG	P	G
*	ACETONE	VG	P	G	LACQUER THINNERS	F	P	G
	AMMONIUM HYDROXIDE	VG	VG	VG	LACTIC ACID (85%)	VG	VG	VG
*	AMYL ACETATE	P	P	F	LAURIC ACID (36%)	F	VG	VG
	ANILINE	F	P	G	LINOLEIC ACID	P	G	VG
*	BENZALDEHYDE	F	G	F	LINSEED OIL	P	VG	VG
*	BENZENE	F	P	F	MALEIC ACID	VG	VG	VG
	BUTYL ACETATE	F	P	G	METHYL ALCOHOL (METHANOL)	VG	VG	VG
	BUTYL ALCOHOL	VG	VG	VG	METHYLAMINE	F	G	F
	CARBON DISULFIDE	F	F	F	METHYL BROMIDE	F	F	G
*	CARBON TETRACHLORIDE	P	G	F	* METHYL CHLORIDE	P	P	P
	CASTOR OIL	P	VG	F	* METHYL ETHYL KETONE (MEK)	G	P	G
*	CHLOROBENZENE	P	P	F	* METHYL ISOBUTYL KETONE (MIBK)	F	P	F
*	CHLOROFORM	P	P	G	METHYL METHACRYLATE	G	F	G
	CHLORONAPHTHALENE	P	F	F	MONOETHANOLAMINE	G	VG	VG
	CHROMIC ACID 50%	P	F	F	MORPHOLINE	VG	G	VG
	CITRIC ACID 10%	VG	VG	VG	NAPHTHALENE	F	G	G
	CYCLOHEXANOL	F	VG	G	NAPHTHAS, ALIPHATIC	F	VG	VG
*	DIBUTYL PHTHALATE	P	G	G	NAPHTHAS, AROMATIC	P	G	G
	DIESEL FUEL	P	VG	G	* NITRIC ACID	F	F	G
	DIISOBUTYL KETONE (DIBK)	F	P	P	NITROMETHANE (95.5%)	P	F	F
	DIMETHYLFORMAMIDE	F	G	F	NITROPROPANE (95.5%)	P	F	F
	DIOCTYL PHTHALATE	P	VG	G	OCTYL ALCOHOL (OCTANOL)	VG	VG	VG
	DIOXANE	G	G	VG	OLEIC ACID	F	VG	VG
	EPOXY RESINS, DRY	VG	VG	VG	OXALIC ACID	VG	VG	VG
*	ETHYL ACETATE	F	F	G	PALMITIC ACID	VG	VG	VG
	ETHYL ALCOHOL (ETHANOL)	VG	VG	VG	PERCHLORIC ACID (60%)	F	G	VG
	ETHYL ETHER	G	G	VG	PERCHLOROETHYLENE	P	G	F
*	ETHYLENE DICHLORIDE	P	P	F	PETROLEUM DISTILLATES (NAPHTHA)	P	VG	G
	ETHYLENE GLYCOL	VG	VG	VG	PHENOL	F	F	VG
	FORMALDEHYDE	VG	VG	VG	PHOSPHORIC ACID	G	VG	VG
	FORMIC ACID	VG	VG	VG	POTASSIUM HYDROXIDE	VG	VG	VG
	FREON 11	P	G	G	PROPYL ACETATE	F	F	G
	FREON 12	P	G	G	PROPYL ALCOHOL	VG	VG	VG
	FREON 21	P	G	G	PROPYL ALCOHOL (ISO)	VG	VG	VG
	FREON 22	P	G	G	SODIUM HYDROXIDE	VG	VG	VG
*	FURFURAL	G	G	G	STYRENE	P	F	P
	GASOLINE, LEADED	P	VG	G	STYRENE (100%)	P	F	P
	GASOLINE, UNLEADED	P	VG	G	SULFURIC ACID	G	G	G
	GLYCERINE	VG	VG	VG	TANNIC ACID (65%)	VG	VG	VG
	HEXANE	P	G	F	TETRAHYDROFURAN	F	F	P
	HYDROCHLORIC ACID	G	G	VG	* TOLUENE	P	F	F
	HYDROFLUORIC ACID 48%	G	G	VG	TOLUENE DIISOCYANATE	G	F	F
	HYDROGEN PEROXIDE 30%	G	G	G	* TRICHLOROETHYLENE	F	G	F
	HYDROQUINONE	G	F	G	TRIETHANOLAMINE	G	VG	VG
	ISOOCTANE	P	VG	F	TUNG OIL	P	VG	VG
	ISOPROPYL ALCOHOL	VG	VG	VG	TURPENTINE	F	VG	G
					* XYLENE	P	F	P

* Limited Services VG=Very Good G=Good F=Fair P=Poor (not recommended)

** Neoprene is a trade name for chloroprene

*** This Chemical Resistance Chart is offered as a guide and for reference purposes only. The chemical resistance ratings are based on published research data.